Dunn-Edwards PAINTS

THE #1 CHOICE OF PAINTING PROFESSIONALS®

WALLTONE®
Interior Latex Flat Paint
W 420V

Contains no Ethylene Glycol or other Toxic Air Contaminants — EG-FREE®

DESCRIPTION: WALLTONE® is a quality interior flat paint designed for use on interior walls, ceilings, and other properly prepared and primed surfaces. **WALLTONE** features a flat finish that helps conceal surface imperfections and allows for easy touch-up. **WALLTONE** has good hide and is self-priming on new drywall.

PRODUCT INFORMATION

SOLVENT TYPE
Waterborne

RESIN TYPE
Acrylic copolymer

FINISH (ASTM D 523)
Flat: 0.5–2% on a 60° meter; 1.0–2% on an 85° meter

COLORS
Stock colors: Whisper, Swiss Coffee, Navajo White, Pearl White, and Cottage White. Other colors can be special ordered or store mixed.

TINT BASES
L Tintable White, M Medium

VISCOSITY@77°F/25°C (ASTM D 562)
95–103 KU

MAXIMUM VOC CONTENT
15 g/L (as supplied)

SOLIDS BY VOLUME (ASTM D 2697)
37.0% ± 2%

SOLIDS BY WEIGHT
53.0 ± 2%

WEIGHT PER GALLON (ASTM D 1475)
11.38 lbs.

COMPOSITION BY WEIGHT

Pigment–39.0%		**Vehicle–61.0%**	
*Prime pigments	18.0	Vinyl acrylic resins	12.5
Reinforcing pigments	21.0	Water & additives	48.5

**Prime pigments include titanium dioxide (TiO_2), plus all other pigments directly adding to the hiding power of this paint.*

RECOMMENDED FILM THICKNESS PER COAT
Wet: 4.2 mils Dry: 1.5 mils

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS
Approximately 250–350 sq. ft. per gallon, depending on surface conditions.

THINNING RECOMMENDATIONS
Brush application: Up to 1/2 pint of water per gallon
Roller application: Do not thin
Spray application: Up to 1 pint of water per gallon

AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)
To touch: 30–60 minutes
Recoat: 2–4 hours

APPLICATION EQUIPMENT
Brush, roller, airless spray

PACKAGING
One-gallon, five-gallon containers

STORAGE
Store in a dry area. Protect from freezing. Extreme temperatures may cause paint to become unusable. For example: freezing and thawing may cause paint to gel, and high heat may cause solid skin to form.

CLEANUP
Warm, soapy water

DISPOSAL
For information on local options to dispose of unwanted, leftover paint, call 800-CLEANUP, or log onto www.cleanup.org.

CONFORMS TO
Master Painters Institute (MPI) #53
Green Seal's Standard GS-11 & LEED requirements
Section 01350/CHPS requirements

MATERIAL SAFETY DATA SHEET
Form #1

SURFACE PREPARATION
All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded, cleaned, and spot-primed with a suitable primer or sealer. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS
- CAUTION: Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call EPA's National Lead Information Hotline at 1-800-424-LEAD, or log onto www. epa.gov/lead or/asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Allow all skim-coats to cure for 3 days before sealing.
- Do not apply when the air or surface temperature is below 50°F.

PRIMERS

DRYWALL	
Textured: Untextured: Skim-coated:	**Self-priming**
MASONRY	
Plaster: Tilt-up concrete: Poured-in-place: Brick:	**Super-Loc® (W 718)**, **Eff-Stop® (W 709)** or **Acri-Loc® (W 6232)**
Concrete block:	**Blocfil (W 304** or **W 305)** or **Concrete Block Filler (W 315)**
Smooth trowel:	**Super-Loc® (W 718)** or **Enduraseal® (W 360)**
WOOD	
Trim, doors:	**Unikote (W 707V)**, **Ultra-Grip® (W 715)** or **Inter-Kote™ (W 6325)**
SYNTHETIC WOOD	
Masonite: Hardboard:	**Unikote (W 707V)**, **Ultra-Grip® (W 715)** or **Inter-Kote™ (W 6325)**
METAL	
Ferrous:	**Corrobar® (43-5)**, **Galv-Alum™ (43-7)**, **Bloc-Rust® (43-4)** or **Ultra-Grip® (W 715)**
Non-ferrous:	**Ultra-Grip® (W 715)** or **Galv-Alum™ (43-7)**

 ©DUNN-EDWARDS CORPORATION • 4885 E. 52nd Place, Los Angeles, CA 90040 • (888) DEPAINT • dunnedwards.com

GALV-ALUM™ is a trademark of BIEC International, Inc. used under license by Dunn-Edwards Corporation.