



APPLY A HIGHER STANDARD™

SUPREMA®

Interior Flat Paint SPMA10



≤ 50 g/L VOC**

SUPREMA® Flat is an ultra-premium interior, ultra-low VOC, acrylic paint that combines exceptional hide with superior stain resistance and washability. **SUPREMA Flat** provides long-lasting protection, applies easily, dries quickly and has low odor. It is ideal for high-end residential and commercial projects, such as schools and hospitals, where self-priming, ultra-low VOC products are preferred.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne | **RESIN TYPE:** Copolymer

FINISH (ASTM D 523): Flat: 2–3% on a 60° meter; 2–3% on an 85° meter

COLORS: Stock colors: Swiss Coffee and Black. Other colors can be special ordered or store mixed.

TINT BASES: L Tintable White, M Medium, U Ultra Deep

VISCOSITY@77°F/25°C (ASTM D 562): 95–105 KU

MAXIMUM VOC CONTENT 50 g/L (as supplied) | **MAXIMUM RAVOC** (Reactivity-Adjusted VOC) 25 g/L

SOLIDS BY VOLUME (ASTM D 2697) 41.0% ± 2% | **SOLIDS BY WEIGHT** 57.0% ± 2%

WEIGHT PER GALLON (ASTM D 1475): 11.83 lbs.

COMPOSITION BY WEIGHT

Pigment—42.6% | **Vehicle—57.4%**
 *Prime pigments 20.5 | Resin solids 13.5
 Reinforcing pigments 22.1 | Water & additives 43.9

*Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.

RECOMMENDED FILM THICKNESS PER COAT

Wet: 3.7 mils | Dry: 1.5 mils

PERFORMANCE SPECIFICATION

Scrubability Results: >1000 cycles | **ASTM D2486; no shim**

Burnish Resistance Results: < 2 unit gloss change in 85° sheen |

ASTM D6736-08; 50 Cycles

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS

Approximately 400–475 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)

To touch: 1–2 hours | Recoat: 2–4 hours

Dry times and recoat times are temperature, humidity and film thickness dependent.

APPLICATION EQUIPMENT: Brush, roller, airless spray

AIRLESS SPRAY	BRUSH	ROLLER
PRESSURE: 1800-2500 psi TIP: .013"-.017"	Nylon/Polyester	Smooth Surfaces: ¼" - ⅝" nap Semi-Smooth Surfaces: ⅜" - ½" nap

PACKAGING: Quart, one-gallon, five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO:

- ARB 2007/2022 SCM & CALGreen 2022
- CA Section 01350
- LEED v4/4.1
- SCAQMD Rule 1113
- CA Extended Producer Responsibility
- EPD
- MIR, HPD
- MPI Approved Product #53
- CRGI Green Wise Certified

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SURFACE PREPARATION: SUPREMA Flat is self priming on most surfaces.

For previously painted surfaces that are properly repaired as needed, one (1) coat may be sufficient. For properly prepared new surfaces, two (2) coats are typically required. All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- **CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. **EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH.** Wear a NIOSH-approved N100 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call U.S. EPA's lead hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or /asbestos, or contact your state or local Health Agency.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- This paint contains a preservative which inhibits the growth of mildew on surface of this paint film.
- On Level 4 and 5 Drywall Finishes, use **VINYLASTIC® Plus (VNPL00)** thinned with 10% of clean water (3/4 pints per gallon or 1/2 gallon per 5-gallons) for best penetration.
- Do not apply when the air or surface temperature is below 50°F



APPLY A HIGHER STANDARD™

SUPREMA®

Interior Flat Paint SPMA10



≤ 50 g/L VOC**

PRODUCT INFORMATION

PRIMERS

DRYWALL

Textured: } VINYLASTIC® Premium (VNPR00),
 Untextured: } VINYLASTIC® Premium (VNPR00),
 Skim-coated: } VINYLASTIC® Plus (VNPL00)

MASONRY

Plaster: } EFF-STOP® Premium (ESPR00),
 Tilt-up concrete: } EFF-STOP® Select (ESSL00) or
 Poured-in-place: } FLEX-PRIME® Select (FPSL00)
 Brick: }

Concrete block: } Smooth BLOCFIL™ Premium (SBPR00) or
 Smooth BLOCFIL™ Select (SBSL00)

Smooth trowel: } SUPER-LOC® Premium (SLPR00)

WOOD

Doors, trim } DECOPRIME® (DCPR00)

SYNTHETIC WOOD

Masonite: } DECOPRIME® (DCPR00)
 Hardboard: }

METAL

Ferrous: } BLOC-RUST® Premium (BRPR00) or
 ENDURAPRIME® Metal Primer (ENPR00)

Non-ferrous: } ULTRASHIELD® Galvanized Metal Primer (ULGM00),
 BLOC-RUST® Premium (BRPR00) or
 SUPER-LOC® Premium (SLPR00)

Galvanized steel: } ULTRASHIELD® Galvanized Metal Primer (ULGM00) or
 *ULTRA-GRIP® Premium (UGPR00)

**for incidental use on galvanized*

***This product has been tested and certified by Coatings Research Group Inc., an international paint industry-organized ISO-accredited testing laboratory, to meet performance and environmental standards as shown on www.greenwisepaint.com. Dunn-Edwards is a member of CRGI.*

HEALTH & SAFETY CAUTIONS! INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N100 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• KEEP OUT OF REACH OF CHILDREN •

Ingredient (CAS #): Water (7732-18-5); Titanium Dioxide (13463-67-7); Nepheline Syenite (37244-96-5); Copolymer Resin (Proprietary); Pumice (1332-09-8).

⚠ **WARNING:** Cancer and Reproductive Harm – www.P65Warnings.ca.gov