



APPLY A HIGHER STANDARD™

EXQUISITE®

Interior Matte Paint EXQT10



≤ 50 g/L VOC**

EXQUISITE® Matte is a deluxe interior, ultra-low VOC, 100% acrylic matte paint meticulously engineered to be a truly washable, stain, scuff, burnish and color rub-off resistant coating. **EXQUISITE Matte** is easy to apply and is ideal for use on high-end custom residential and premier commercial projects where exceptional performance and refined results are required.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne		RESIN TYPE: 100% Acrylic
FINISH (ASTM D523): Matte: 3–8% on a 60° and 85° meter		
COLORS: Colors can be store mixed or special ordered.		
TINT BASES: L Tintable White, M Medium, U Ultra Deep		
VISCOSITY@77°F/25°C (ASTM D 562): 88–98 KU		
MAXIMUM VOC CONTENT 50 g/L (by ASTM Test Method D 6886)	MAXIMUM RAVOC (Reactivity-Adjusted VOC) 30 g/L	
SOLIDS BY VOLUME (ASTM D 2697) 44.6% ± 2%	SOLIDS BY WEIGHT 61.3 ± 2%	
WEIGHT PER GALLON (ASTM D 1475): 11.93 lbs.		
COMPOSITION BY WEIGHT		
Pigment—42.0%		Vehicle—58.0%
Prime pigments	22.2%	Resin solids.....16.0%
Reinforcing pigments	19.8%	Water & additives42.0%
*Prime pigments include all pigments directly adding to the hiding power of this paint.		

RECOMMENDED FILM THICKNESS PER COAT
Wet: 3.3 mils Dry: 1.5 mils

PERFORMANCE SPECIFICATION

Scrubability Results: >4000 cycles | **ASTM D2486; no shim**
Burnish Resistance Results: < 2 unit gloss change in 85° sheen |
ASTM D6736-08; 50 Cycles
Washability Results: Pass (9.0) | **ASTM D4828; avg of 5 stains**
Cleansability Results: Coffee <2.0 Δe, Nigrosin <1.0 Δe, Graphite <1.5 Δe |
MPI Method

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS
Approximately 425–475 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)
Dry to touch: 30–60 minutes Recoat: 2–4 hours
Dry times and recoat times are temperature, humidity and film thickness dependent.

APPLICATION EQUIPMENT: Brush, roller, airless spray

AIRLESS SPRAY	BRUSH	ROLLER
PRESSURE: 1800–2500 psi TIP: .013"–.017"	Nylon/Polyester	Smooth Surfaces: 1/4" - 3/8" nap Semi-Smooth Surfaces: 3/8" - 1/2" nap

PACKAGING: Quart, one and five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See Paint Storage Best Practices Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO:

- ARB 2007/2020 SCM & CALGreen 2022
- CA Section 01350
- LEED v4/4.1
- SCAQMD Rule 1113
- CA Extended Producer Responsibility
- MIR, HPD
- MPI Approved Product #53, #138, #142
- CRGI Green Wise Certified

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: **EXQUISITE Matte** is self priming on most surfaces. For previously painted surfaces that are properly repaired as needed, one (1) coat may be sufficient. For properly prepared new surfaces, two (2) coats are typically required. All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- **CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH approved N100 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call EPA's National Lead Information Hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or / asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- This paint contains a preservative that inhibits the growth of mildew on the surface of the dry paint film.
- On Level 4 and 5 Drywall Finishes, use **VINYLASTIC® Plus (VNPL00)** thinned with 10% of clean water (3/4 pints per gallon or 1/2 gallon per 5-gallons) for best penetration. When using **EXQUISITE Matte (EXQT10)**, it is recommended that an additional coat of **VINYLASTIC® Premium (VNPR00)** or **ULTRA-GRIP® Premium (UGPR00)** be applied to achieve a smooth, uniform sheen and finish.
- Do not apply when the air or surface temperature is below 50°F.



APPLY A HIGHER STANDARD™

EXQUISITE®

Interior Matte Paint EXQT10



≤ 50 g/L VOC**

PRODUCT INFORMATION

PRIMERS

DRYWALL

Textured: } VINYLASTIC® Premium (VNPR00),
 Untextured: } VINYLASTIC® Premium (VNPR00),
 Skim-coated: } VINYLASTIC® Plus (VNPL00)
 (see Special Instructions)

MASONRY

Plaster: } EFF-STOP® Premium (ESPR00),
 Tilt-up concrete: } EFF-STOP® Select (ESSL00) or
 Poured-in-place: } FLEX-PRIME® Select (FPSL00)
 Brick: }

Concrete block: } Smooth BLOCFIL™ Premium (SBPR00) or
 Smooth BLOCFIL™ Select (SBSL00)

Smooth trowel: } SUPER-LOC® Premium (SLPR00)

WOOD

Doors, trim } DECOPRIME® (DCPR00) or,
 ULTRA-GRIP® Premium (UGPR00)

SYNTHETIC WOOD

Masonite: } DECOPRIME® (DCPR00)
 Hardboard: }

METAL

Ferrous: } BLOC-RUST® Premium (BRPR00) or
 ENDURAPRIME® Metal Primer (ENPR00)

Non-ferrous: } ULTRASHIELD® Galvanized Metal Primer (ULGM00),
 BLOC-RUST® Premium (BRPR00) or
 SUPER-LOC® Premium (SLPR00)

Galvanized steel: } ULTRASHIELD® Galvanized Metal Primer (ULGM00) or
 *ULTRA-GRIP® Premium (UGPR00)

**for incidental use on galvanized*

***This product has been tested and certified by Coatings Research Group Inc., an international paint industry-organized ISO-accredited testing laboratory, to meet performance and environmental standards as shown on www.greenwisepaint.com. Dunn-Edwards is a member of CRGI.*

HEALTH & SAFETY: CAUTIONS! INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N100 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• KEEP OUT OF REACH OF CHILDREN •

Ingredient (CAS #): Water (7732-18-5); Titanium Dioxide (13463-67-7); Ceramic Microsphere (66402-68-4); Copolymer Resin (Proprietary); Silica Gel (112926-00-8).

⚠ **WARNING!** Cancer and Reproductive Harm – www.P65Warnings.ca.gov