



# Dunn's® Ceiling Paint Interior Dead Flat DICP00-0-LHW8



Dunn's Ceiling Paint Interior Dead Flat is a premium, Zero VOC, low odor paint specifically designed for ceilings on residential, commercial and institutional projects that require a dead flat finish. Dunn's Ceiling Paint Interior Dead Flat provides excellent hide, sheen uniformity and touch-up, dries fast, is spatter resistant and can be applied by brush, roll or spray.

## PRODUCT INFORMATION

**SOLVENT TYPE:** Waterborne | **RESIN TYPE:** Copolymer

**FINISH** (ASTM D 523): Flat: 1.5-2.5% on a 60° meter; 1.0-2.0% on a 85° meter

**COLORS:** LHW8 Classic White, Tintable.

**VISCOSITY@77°F/25°C** (ASTM D 562): 100–110 KU

**MAXIMUM VOC CONTENT** <5 g/L (by ASTM Test Method D 6886) | **MAXIMUM RAVOC** (Reactivity-Adjusted VOC) <5 g/L

**NOTE:** "Zero VOC" means "No organic solvents added" (Trace amounts of VOC may be present as residual components of other ingredients. Dunn-Edwards uses Zero VOC colorants; other additives may increase VOC emissions.)

**SOLIDS BY VOLUME** (ASTM D 2697) 35.1% ± 2% | **SOLIDS BY WEIGHT** 52.6% ± 2%

**WEIGHT PER GALLON** (ASTM D 1475): 11.60 lbs.

### COMPOSITION BY WEIGHT

<b>Pigment—44%</b>	<b>Vehicle—56%</b>
*Prime pigments .....12.5	Acrylic copolymer resin.....5.9
Reinforcing pigments .....31.5	Water & additives .....50.1

\*Prime pigments include titanium dioxide (TiO<sub>2</sub>), plus all other pigments directly adding to the hiding power of this paint.

### RECOMMENDED FILM THICKNESS PER COAT

Wet: 4.3 mils | Dry: 1.5 mils

### PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS

Approximately 325–375 sq. ft. per gallon, depending on surface conditions and application techniques.

**THINNING RECOMMENDATION:** This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

### AVERAGE DRY TIME@77°F/25°C

To touch: 30–60 minutes | Recoat: 1–2 hours  
Dry times and recoat times are temperature, humidity and film thickness dependent.

### APPLICATION EQUIPMENT:

AIRLESS SPRAY	BRUSH	ROLLER
<b>PRESSURE:</b> 1800-2500psi <b>TIP:</b> .015"-.017"	Nylon/Polyester	1/4"-1" Emerald Series Pro-White roller cover

**PACKAGING:** One-gallon, five-gallon containers

**STORAGE:** Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

**CLEANUP:** Warm, soapy water

**DISPOSAL:** For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit [www.dunnedwards.com](http://www.dunnedwards.com). **Do not mix with other products.**

**CONFORMS TO:** ARB 2007/2020 SCM & CALGreen 2022; CDPH Standard Method v1.2; LEED v4 & v4.1 EQ Credit: Low-Emitting Material; CRGI Green Wise Certified Gold

**SAFETY DATA SHEET:** Available at [www.dunnspaints.com](http://www.dunnspaints.com)

**SURFACE PREPARATION:** All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peel-ing, or chalky paint by sanding, scraping, or other appropriate methods.

Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion. For special instructions, and recommendations on specialty primers, sealers, and undercoaters.

### SPECIAL INSTRUCTIONS

- **CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH-approved N100 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call U.S. EPA's lead hotline at 1-800-424-LEAD, or visit [www.epa.gov/lead](http://www.epa.gov/lead) or /asbestos, or contact your state or local Health Agency.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Prime all stains with a stain blocking primer.
- Do not apply when the air or surface temperature is below 50°F.

### PRIMERS

#### ACOUSTIC CEILING

Spray texture: **Self-priming** (first coat)  
Acoustic tile: **Self-priming** (see Special Instructions)

#### METAL

Ferrous:	} <b>Dunn's® Interior/Exterior Multi-Surface Primer (DPMP00-0-WH)</b>
Non-ferrous:	
Galvanized steel:	

\*for incidental use on galvanized

**HEALTH & SAFETY CAUTIONS:** INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N100 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

#### • KEEP OUT OF REACH OF CHILDREN •

Ingredient (CAS #): Water (7732-18-5); Feldspar (68476-25-5); Titanium Dioxide (13463-67-7); Kaolin Calcined (92704-41-4); Copolymer Resin (Proprietary); Quartz (14808-60-7).

⚠ **WARNING:** Cancer and Reproductive Harm – [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)