



# PRO-COM<sup>®</sup> 3500

## Interior Flat Paint

### PC3510



APPLY A HIGHER STANDARD<sup>®</sup>

**PRO-COM<sup>®</sup> 3500 Interior Flat Paint** is a professional interior paint that is ideal for commercial projects, such as multi-tenant housing, schools, hotels, or hospitals. **PRO-COM 3500** provides very good hide, touch-up and sheen uniformity on new drywall for interior walls and ceilings. **PRO-COM 3500** is self-priming on properly prepared new drywall.

## PRODUCT INFORMATION

**SOLVENT TYPE:** Waterborne | **RESIN TYPE:** Copolymer

**FINISH** (ASTM D 523): Flat: 1.0–1.5% on a 60° meter; 1.0–1.5% on an 85° meter

**COLORS:** All colors can be special ordered or store mixed.

**TINT BASES:** L Tintable White, U Ultra Deep

**VISCOSITY@77°F/25°C** (ASTM D 562): 97–107 KU

<b>MAXIMUM VOC CONTENT</b> 5 g/L (as supplied)	<b>MAXIMUM RAVOC</b> (Reactivity-Adjusted VOC) 5 g/L
---	---

<b>SOLIDS BY VOLUME</b> (ASTM D 2697) 29.7% ± 2%	<b>SOLIDS BY WEIGHT</b> 45.6% ± 2%
---	---------------------------------------

**WEIGHT PER GALLON** (ASTM D 1475): 11.03 lbs.

### COMPOSITION BY WEIGHT

<b>Pigment—37.8%</b>		<b>Vehicle—62.2%</b>	
*Prime pigments .....	11.7	Resin solids .....	5.8
Reinforcing pigments .....	26.1	Water & additives .....	56.4

\*Prime pigments include titanium dioxide (TiO<sub>2</sub>), plus all other pigments directly adding to the hiding power of this paint.

### RECOMMENDED FILM THICKNESS PER COAT

Wet: 5.0 mils                      Dry: 1.5 mils

### PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS

Approximately 250–300 sq. ft. per gallon, depending on surface conditions and application techniques.

**THINNING RECOMMENDATION:** This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

### AVERAGE DRY TIME@77°F/25°C

To touch: 30–60 minutes                      Recoat: 2–4 hours  
Dry times and recoat times are temperature, humidity and film thickness dependent.

**APPLICATION EQUIPMENT:** Brush, roller, airless spray

AIRLESS SPRAY	BRUSH	ROLLER
<b>PRESSURE:</b> 1800-2500 psi	Nylon/Polyester	Smooth Surfaces: 3/8" - 1/2" nap Semi-Smooth Surfaces: 1/2" - 3/4" nap
<b>TIP:</b> .015"-.019"		

**PACKAGING:** One-gallon, five-gallon containers

**STORAGE:** Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at [dunnedwards.com](http://dunnedwards.com) for more information.

**CLEANUP:** Warm, soapy water

**DISPOSAL:** For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit [www.dunnedwards.com](http://www.dunnedwards.com). **Do not mix with other products.**

### CONFORMS TO:

• ARB 2007/2022 SCM & CALGreen 2022	• CA Extended Producer Responsibility
• LEED v4/4.1	• MIR, HPD
• SCAQMD Rule 1113	

**SAFETY DATA SHEET:** Available at [www.dunnedwards.com](http://www.dunnedwards.com)

**SURFACE PREPARATION:** **PRO-COM 3500** is self-priming on most surfaces. For previously painted surfaces that are properly repaired as needed, one (1) coat may be sufficient. For properly prepared new surfaces, two (2) coats are typically required. All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

### SPECIAL INSTRUCTIONS

- **CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH-approved N100 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call U.S. EPA's lead hotline at 1-800-424-LEAD, or visit [www.epa.gov/lead](http://www.epa.gov/lead) or / asbestos, or contact your state or local Health Agency.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- On Level 4 and 5 Drywall Finishes, thin **VINYLASTIC<sup>®</sup> Plus (VNPL00)** with 10% of clean water (3/4 pints per gallon or 1/2 gallon per 5-gallons) for best penetration
- When touching up **PRO-COM 3500** Paint, use the same application method originally used and use paint from the same batch. If spray touch-up is not practical, use a good quality 1/2" nap synthetic roller for best sheen uniformity, especially on smooth walls. Apply a full coat at original application viscosity. Vertical strokes are preferred over horizontal. Avoid feathering (excessive rolling or brushing) into the original painted areas around the touch-up. For more information, see Dunn-Edwards Technical Bulletin on "Touch-Up".
- Do not apply when the air or surface temperature is below 50°F



APPLY A HIGHER STANDARD®

# PRO-COM® 3500

## Interior Flat Paint

### PC3510



### PRODUCT INFORMATION

#### PRIMERS

##### DRYWALL

Textured: } VINYLASTIC® Premium (VNPR00),  
Untextured: } VINYLASTIC® Premium (VNPR00),  
Skim-coated: } VINYLASTIC® Plus (VNPL00)  
(see *Special Instructions*)

##### MASONRY

Plaster: } SUPER-LOC® Premium (SLPR00),  
Tilt-up concrete: } EFF-STOP® Premium (ESPR00) or  
Poured-in-place: } EFF-STOP® Select (ESSL00)  
Brick:  
  
Concrete block: } Smooth BLOCFIL™ Premium (SBPR00) or  
Smooth BLOCFIL™ Select (SBSL00)  
  
Smooth trowel: } PRO-COM® Masonry Primer (PCMA00) or  
SUPER-LOC® Premium (SLPR00)

##### WOOD

Doors, trim: } DECOPRIME® (DCPR00),  
ULTRA-GRIP® Premium (UGPR00) or  
ULTRA-GRIP® Select (UGSL00)

##### SYNTHETIC WOOD

Masonite: } DECOPRIME® (DCPR00),  
Hardboard: } ULTRA-GRIP® Premium (UGPR00) or  
ULTRA-GRIP® Select (UGSL00)

##### METAL

Ferrous: } BLOC-RUST® Premium (BRPR00) or  
ENDURAPRIME® Rust-Preventative Metal Primer  
(ENPR00)  
  
Non-ferrous: } ENDURAPRIME® Galvanized Metal Primer (ENGM00) or  
BLOC-RUST® Premium (BRPR00) or  
SUPER-LOC® Premium (SLPR00)  
  
Galvanized steel: } ENDURAPRIME® Galvanized Metal Primer (ENGM00) or  
\*ULTRA-GRIP® Premium (UGPR00)

*\*for incidental use on galvanized*

**HEALTH & SAFETY CAUTIONS!** INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N100 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• KEEP OUT OF REACH OF CHILDREN •

Ingredients (CAS #): Water (7732-18-5); Limestone (1317-65-3); Titanium Dioxide (13463-67-7); Copolymer Resin (Proprietary); Kaolin, Calcined (92704-41-1); Quartz (14808-60-7).

**WARNING:** Cancer and Reproductive Harm – [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)